

Features	Test Method	Value	
Percentage of Tiles without Defects	ISO 10545-2	≥95%	
Work Size	ISO 10545-2	± 0.5%/±2.0mm	
Straightness of Sides	ISO 10545-2	± 0.3%/±1.5mm	
Rectangularity	ISO 10545-2	± 0.5%/±2.0mm	
Edge Curvature	ISO 10545-2	-0.3/+0.5%/-1.5/+2.0mm	
Centre Curvature	ISO 10545-2	-0.3/+0.5%/-1.5/+2.0mm	
Warpage	ISO 10545-2	± 0.5%/±2.0mm	
Thickness	ISO 10545-2	± 10%/±1.5mm	
Water Absorption	ISO 10545-3	E>10% min 9%	
Modulus of Rupture	ISO 10545-4	e≥7.5mm	e<7.5mm
		≥600N	≥200N
Breaking Strength	ISO 10545-4	Media ≥12 N/mm ²	Media ≥15 N/mm ²
Linear Thermal Expansion	ISO 10545-8	5.9x10 ⁻⁵ °K ⁻¹	
Resistance to Thermal Shock	ISO 10545-9	Resistant	
Crazing Resistance	ISO 10545-11	Resistant	
Chemical Resistance	ISO 10545-13	Household	Low Concentration
		GA	GLA
Stain Resistance	ISO 10545-14	5	

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy Finish
- 8mm Thickness
- Pressed Edge
- V2 - Slight Shading Variation
- Frost Resistance = No

