

Features	Test Method	Value
<b>Water Absorption</b>	ASTM C373	≤0.1%
<b>Thickness Dimension</b>	ASTM C499	≤±0.04 Inc.
<b>Facial Dimension</b>	ASTM C499	≤ ± 0.25%
<b>Warpage Average Diagonal</b>	ASTM C485	≤ ± 0.40%
<b>Warpage Average Edge</b>	ASTM C485	≤ ± 0.40%
<b>Wedging</b>	ASTM C502	≤ ± 0.25%
<b>Bond Strength</b>	ASTM C482	≥ 200 psi
<b>Breaking Strength</b>	ASTM C648	≥ 400 lb.
<b>Hardness (Mohs)</b>	Scratch Test (No regulated)	≥ 7
<b>Visible Abrasion Resistance for Glazed Tiles</b>	ASTM C1027	Class 4
<b>Frost Resistance</b>	ASTM C1026	Resistant
<b>Chemical Resistance</b>	ASTM C650	Class A
<b>Stain Resistance</b>	ASTM C1378	Class A*
<b>DCOF</b>	BOT 3000	≥0.48*
<b>Aesthetic Classification</b>	Visual Evaluation Shade & Texture	V2
<b>Recycled Material</b>	-	≥40%



This product is GREENGUARD® certified and will contribute to USGBC registered LEED projects. It will also contribute to the ANSI approved NAHB Green Building Standard ICC 70.

\*All values given are for matte or honed material. No values are given for polished material. GENROSE does not recommend polished surfaces in areas subject to exposure from grease, oil or water.

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide.

**Product Info:**

- Color Body Porcelain Tile
- Honed | Polished Finish
- 8mm Thicknesses
- Rectified Edge
- Frost Resistance = Yes
- PEI Rating = 4
- V2 - Slight Shading Variation



[www.genrose.com](http://www.genrose.com)