




Features	Test Method	Value
Length and Width	ASTM C499	Complies with ANSI A 137.1 TAB. 10
Thickness		
Straightness of Sides		
Surface Flatness		
Rectangularity		
Surface Quality		>95%
Water Absorption	ISO 10545-3	≤0.05%
Modulus of Rupture / Bending Strength	ISO 10545-4	≥ 35 N/mm ²
Breaking Strength	ISO 10545-4	≥ 1300 N
Surface Hardness (Mohs)	EN 101	7
Resistance to Surface Abrasion	ISO 10545-7	Class 4
Coefficient of Linear Thermal Expansion	ISO 10545-8	< 7.1 x 10 ⁻⁶ °C ⁻¹
Thermal Shock Resistance	ISO 10545-9	Resistant
Crazing Resistance	ISO 10545-11	Resistant
Frost Resistance	ISO 10545-12	Resistant
Chemical Resistance (Domestic)	ISO 10545-13	A
Chemical Resistance (Low Concentration)		LA
Chemical Resistance (High Concentration)		HA
Stain Resistance	ISO 10545-14	Class 5
Slip Resistance	ANSI A137.1	DCOF 0.56
Recycled Content	-	> 40%
VOC Emissions	-	Zero VOC

This product will contribute to USGBC registered LEED projects.
It will also contribute to the ANSI approved NAHB Green Building Standard ICC 700.

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Disclaimer: DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.

Product Info:

- Glazed Porcelain Tile
- Natural | Semi-Polished Finishes
- 9mm | 20mm Thicknesses
- Rectified Edge
- PEI Rating = 4
- Frost Resistance = Yes



www.genrose.com