



Features	Test Method	Value
Length and Width	ISO 10545-2	± 0.5% ± 2mm
Thickness	ISO 10545-2	± 5% ± 0.5mm
Straightness of Sides	ISO 10545-2	± 3% ± 1.5 mm
Rectangularity	ISO 10545-2	± 3% ± 1.5mm
Surface Flatness	ISO 10545-2	± 0.5% ± 0.5mm
	ASTM C 485	Warpage Diagonal/Edge ±0.4%
Water Absorption	ISO 10545-3	≤ 0.3%
Bending Strength	- ISO 10545-4	≥ 35 N/mm²
Breaking Strength		≥ 1300 N
Abrasion Resistance	ISO 10545-7	Class 4
Coefficient of Linear Thermal Expansion	ISO 10545-8	Test Method Available
Thermal Shock Resistance	ISO 10545-9	Resistant
Crazing Resistance	ISO 10545-11	Resistant
Frost Resistance	ISO 10545-12	Resistant
Household Chemical Resistance	ISO 10545-13	Class A
Acid and Base Resistance		Class LA Class HA
Stain Resistance	ISO 10545-14	Class 5
D.C.O.F. (WET) Slip Resistance	ANSI A137.1	0.45

This product will contribute to USGBC registered LEED projects. It will also contribute to the ANSI approved NAHB Green Building Standard ICC 700.

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Disclaimer: DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.

Product Info:

- Glazed Porcelain Tile
- Natural Finish
- Pressed Edge
- V4 Extreme Variation
- Frost Resistance = Yes







www.genrose.com