

Features	Test Method	Value	
Length	ISO 10545-2	- 0.04% / +0.08%	
Width	ISO 10545-2	± 0.25%	
Thickness	ISO 10545-2	1.25%	
Rectangularity in Length	ISO 10545-2	± 0.16%	
Rectangularity in Width	ISO 10545-2	± 0.12%	
Straightness of Sides	ISO 10545-2	± 0.04%	
Center Curvature	ISO 10545-2	-0.19%	
Edge Curvature	ISO 10545-2	-0.20%	
Warpage	ISO 10545-2	± 0.04%	
Surface Quality	ISO 10545-2	100% without defects	
Water Absorption	ISO 10545-3	≤ 18.0%	
Modulus of Rupture	ISO 10545-4	21 N/mm ²	
Breaking Load	ISO 10545-4	300 N	
Breaking Strength	ISO 10545-4	860 N	
Linear Thermal Expansion	ISO 10545-8	5.9 x 10 ⁻⁶ °K ⁻¹	
Resistance to Thermal Shock	ISO 10545-9	Resistant	
Crazing Resistance	ISO 10545-11	Resistant	
Chemical Resistance	ISO 10545-13	Household	Low Concentration
		GA	GLA
Stain Resistance	ISO 10545-14	5	
Recycled Material	-	≥18%	

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy Finish
- 8mm Thickness
- Pressed Edge
- V1 - Uniform Appearance
- Frost Resistance = No


www.genrose.com